



Пленка перфорированная DLC OWV

(One Way Vision)

Product Introduction:

Exterior window mount perforated 120micron calendared white & black vinyl with semi-removable clear adhesive. 60% Print Surface for detailed graphics and 40% view through.

Test Items	Units	Test method	Average value
Thickness-PVC	Micron	ISO534	120±10
Weight-Liner	g/m ²	GB4669-1995	120±10
Weight- Finished Products	g/m ²	GB4669-1995	220±20
Gloss Rate-60 °	%	ISO2813	20±10%
Whiteness	%	CI2 Ganz ≥85	
Initial Adhesion	N/25mm	FTM-1 ≥3	
Adhesion 24h-180° peel	N/25mm	FTM-1 ≥4	
Opacity	%	ISO2471	60
Dimensional stability	mm	DIN 38464 ≤1.0	
Tensile Strength-MD	N/50mm	DIN53354 ≥35	
Tensile Strength-CD	N/50mm	DIN53354 ≥25	
Tearing Strength-MD	N	DIN53356 ≥5	
Tearing Strength-CD	N	DIN53356 ≥7	
Flammability			Self extinguishing
Service Temperature °C			-20~+70
Best Printing Temperature °C			23±2; 50±5%RH
Ink temperature °C			18~28
Preheating temperature °C			30
Shelf Life	Stored at 20-25 °C/50-55 % RH		1 year
Durability, unprinted	Vertical exposure		1 year
Ink recommendations	Eco-solvent  Solvent		